



0846/0876 Series Window & Door Siliconized Acrylic Caulk:

- **What is the base chemistry for 35 Yr Window & Door Sealants?** Siliconized Acrylic Terpolymer Blend.
- **Are the 0846 Series White & Colors & 0876 Clear compliant to any performance specifications?** Yes. White & Colors are compliant to ASTM C834-00 Type P (pigmented formulations) & Clear is compliant to ASTM C834-00 Type C (clear formulations).
- **What colors is the 0846 Series available in?** White, Almond, Cedar, Dark Brown, Gray & Black.
- **Are the 0846 Series Sealants & 0876 water clean up?** Yes.
- **Are the caulks suitable for interior or exterior applications?** Yes.
- **Are the sealants paintable?** Yes. White is paintable following about 2 hrs; longer drying time may be required in conditions of cooler temperatures & higher humidity. The colors are also paintable, should a color change be desired @ a future point. Clear is paintable following full transition from white to clear.
- **Does 0876 Clear apply clear?** No; the acrylic clear applies white & turns clear within about 14 days, depending upon climatic conditions, bead size & porosity of substrate.
- **Are the 0846/0876 Series 35 Year Sealants suitable for below-grade applications?** No.
- **What is the recommended application temperature range?** 40F & rising, to 90F.
- **Are the 0846/0876 Series 35 Year Sealants UL Listed?** No.
- **Are the 0846/0876 Series 35 Year Sealants mildew resistant?** Yes.